PS09 - Remove Heavy Porcelain Wax

Remove Heavy Porcelain Wax from Porcelain or Ceramic Tiles

PRODUCT: XTREMECLEAN with MICROSCRUB

EQUIPMENT:

- AquaBug Cleaning Kit;
- Scrub pad or brush;
- Broom
- Bucket
- Clean water;
- Cotton towels.
- Wet vac;
- Optional: Scrub machine

PRECAUTIONS:

1. Read entire label, SDS & technical bulletin before using;
2. Wear appropriate skin & eye protection;
3. Use when surface temperature is between 4°C & 32°C;
4. Do NOT allow contact with non recommended surfaces;
5. Do NOT mix with other chemicals;
6. Regular use of high alkaline cleaners will affect the performance of sealers, coatings & floor finishes;
7. May lighten some dark grouts & affect some grout colourants.
8. Do NOT use undiluted. The undiluted product can dull or discolour some surfaces;
9. Do NOT allow product to dry on the surface. Add more product as required to keep wet.

PROCEDURE:

1. Sweep, vacuum, or wipe surface;
2. Dilute XtremeClean with clean water as follows depending on the severity of the problem:
   a) **LIGHT:** Dilute 1 part XtremeClean to 15 parts water.
   (1 litre = 70ml XtremeClean to 930 ml water)
   b) **MODERATE:** Dilute 1 part XtremeClean to 10 parts water
   (1 litre = 100ml XtremeClean to 900 ml water)
   c) **HEAVY:** Dilute 1 part XtremeClean to 5 part water ;
   (1 litre = 200ml XtremeClean to 800 ml water)
   d) **STRIPPING:** Dilute 1 part XtremeClean to 3 parts water;
   (1 litre = 330ml XtremeClean to 670 ml water)
3. Carefully apply the solution to surface with a sponge or a mop;
4. Allow minimum dwell time of 10 minutes. Longer dwell time may be required;
5. DO NOT ALLOW PRODUCT TO DRY ON THE SURFACE - ADD MORE PRODUCT AS REQUIRED;
6. After the dwell time, add MicroScrub to standing soluytion then scrub with a white nylon pad, scrub brush or scrub machine;
7. Remove the dirty solution with a wet vac or mop;
8. Rinse thoroughly with clean water;
9. Repeat the process as necessary.

Note A: For extreme heavy wax coatings, see use Strip-It as per label instructions

This recommendation is intended as a general guideline. The actual procedure requirements, dilution ratios, dwell time etc may vary depending on type of surface, method of application and severity of the problem.
READ PRODUCT LABEL INSTRUCTIONS, TECHNICAL BULLETIN & SDS THOROUGHLY BEFORE USING. ALWAYS TEST FIRST.
KEEP SURFACE CLEAN AND DRY TO REDUCE THE POSSIBILITY OF SLIP & FALL ACCIDENTS AND INJURIES

Aqua-Seal STS - Technical Support
P: +61 2 9521 4000 Monday to Friday 9.00am - 4.00pm
E: sales@aqua-seal.com.au www.aqua-seal.com.au

© Copyright July 2019