PS27 - Darken Light or Faded Grout

To Darken and Seal Existing Grout

PRODUCT: **ENHANCE'N'SEAL ™**

EQUIPMENT:

- AquaBug Cleaning Kit;
- Sponge or brush;
- Broom
- Bucket
- Cotton or paper towels.

PRECAUTIONS:

1. Read entire label, SDS & technical bulletin before using;
2. Wear appropriate skin & eye protection & use in a ventilated area;
3. Surface must be clean, dry & free from any sealers & coatings;
4. Use when surface temperature is between 4°C and 32°C;
5. Do NOT allow sealer to drip or leave drip marks on the surface;
6. Do NOT use on underside of tile or stone;
7. Do NOT allow product to dry on the surface - remove excess;
8. Once a surface has been enhanced it CANNOT be restored to original look.

PROCEDURE:

1. Sweep, vacuum or wipe surface;
2. Apply Enhance'N'Seal™ to clean, dry grout using a sealer sponge or brush;
3. Take extreme care when applying Enhance'N'Seal™ to grout as it will darken any surrounding porous surfaces. The darkening CANNOT be revered;
4. Ensure even coat & coverage then work product in thoroughly;
5. After 5-10 minutes, wipe the surface COMPLETELY DRY with absorbent paper or cotton towels to remove any excess;
6. DO NOT ALLOW PRODUCT TO DRY ON THE SURFACE;
7. Repeat this process for each application;

PROCEDURE NOTES:

1. For vertical surfaces apply Enhance'N'Seal™ bottom to top and avoid rundown;
2. Porous surfaces will require additional coats. If 2 or more coats are required, allow minimum 30 minutes between coats;
3. 2 hours after the final coat, conduct a test to determine if the surface is properly sealed. Apply a few water droplets to the surface. If the water is easily absorbed then apply an additional coat of sealer. Wait 2 hours and repeat the test.
4. The surface is ready for light traffic after 2 hours. Keep dry for minimum 24 hours. Full cure in minimum 24 hours.

Note A: NOT suitable for epoxy grout
Note B: If grout is patchy or blotchy, use Renue'N'Seal to recolour and seal. See Problem Solver #17 - Recolour Grout.
Note C: Take extreme care when applying Enhance'N'Seal™ to grout as it will darken any surrounding porous surfaces. The darkening **CANNOT** be reversed

This recommendation is intended as a general guideline. The actual procedure requirements, dilution ratios, dwell time etc may vary depending on type of surface, method of application and severity of the problem.
READ PRODUCT LABEL INSTRUCTIONS, TECHNICAL BULLETIN & SDS THOROUGHLY BEFORE USING. ALWAYS TEST FIRST.
KEEP SURFACE CLEAN AND DRY TO REDUCE THE POSSIBILITY OF SLIP & FALL ACCIDENTS AND INJURIES

Aqua-Seal STS™ - Technical Support
P: +61 2 9521 4000 Monday to Friday 9.00am - 4.00pm
E: sales@aqua-seal.com.au www.aqua-seal.com.au

© Copyright July 2019